

DuPont™ Kalrez® Spectrum™ 7075

High Temperature Resistance & Low Compression Set

Technical Information - Rev. 1, July 2019

Product Description

DuPont™ Kalrez® perfluoroelastomer parts are the material of choice for mechanical seals, valves, flanges and other demanding chemical and hydrocarbon processing applications.

Kalrez® Spectrum™ 7075 is positioned in the Kalrez® Spectrum™ family of products which are designed for the chemical processing industry. Compound 7075 offers enhanced physical performance properties including very low compression set (Figure 1).

Typical Physical Properties¹

Color	Black
Hardness ² , Shore A	75
100% Modulus ³ , MPa (psi)	11.23 (1629)
Tensile at Break ³ , MPa (psi)	17.91 (2598)
Elongation at Break ³ , %	160
Compression Set ⁴ , %	
70 hr at 204 °C (400 °F)	10
Compression Set ⁵ , %	
70 hr at 204 °C (400 °F)	13
Max. Service Temp. ⁶ , °C (°F)	327 (620)
Lowest Service Temp. ⁶ , °C (°F)	-18 (-0.4)

¹ Not to be used for specifications

² ASTM D2240 (Pellet test specimens)

³ ASTM D412 (Dumbbell test specimens)

⁴ ASTM D395B, (Pellet test specimens)

⁵ ASTM D395B D395B & D1414, (AS568 K214 O-ring test specimens)


⁶ DuPont proprietary test method; performance will vary with seal design and application specifics

Thermal, Chemical, and Mechanical Performance

Kalrez® Spectrum™ 7075 is designed for general-purpose use as O-rings or custom sealing components in the chemical and hydrocarbon processing industries. It is a carbon black-filled compound with mechanical properties designed for improved sealing performance in temperature cycling applications. 7075 has improved thermal resistance that extends maximum service temperature to 327 °C (620 °F). It is not suggested for use in severe aqueous and amine applications where Kalrez® Spectrum™ 6375 remains the preferred compound. As always, we recommend the specific chemicals, service temperature and pressure be reviewed for the optimal compound selection in each application.

Kalrez® Spectrum™ 7075 offers very low compression set as measured by ASTM D395 to predict heat resistance. DuPont compression set testing extends the standard ASTM 70-hour protocol to include 336 and 672-hour compression set testing, which better predicts long-term O-ring performance. Lower compression set results in improved sealing and longer service life.

Figure 1. Compression Set at 204 °C



Applications

DuPont™ Kalrez® Spectrum™ 7075, with its low compression set, is a great choice for today's smaller and lighter mechanical seals, which are expected to perform as efficiently as larger mechanical seals. The smaller mechanical seal designs, with reduced spring force retention, put additional demands on elastomeric O-rings with reduced cross sections. The smaller cross section O-rings are more prone to compression set which can reduce their functional effectiveness, thereby reducing the operability of the mechanical seal.



Quick connector couplings also benefit from the outstanding compression set of Kalrez® Spectrum™ 7075 and its enhanced temperature cycling capabilities. Combined with low swell in a wide range of chemicals, this compound ensures reliable performance of modern fluids handling systems.

Chemical Resistance to:	DuPont™ Kalrez® Spectrum™ 7075	DuPont™ Kalrez® Spectrum™ 4079	DuPont™ Kalrez® Spectrum™ 6375
Aromatic/Aliphatic Oils	++++	++++	++++
Acids	++++	++++	++++
Bases	++	++	++++
Alcohols	++++	++++	++++
Aldehydes	++++	+++	+++
Amines	++	+	++++
Ethers	++++	++++	++++
Esters	++++	++++	++++
Ketones	++++	++++	++++
Steam/Hot Water	X	X	+++
Strong Oxidizers	++	++	++
Ethylene Oxide	+++	X	++++
Hot Air	++++	++++	+++

++++ = Excellent +++ = Very Good ++ = Good + = Fair X = Not Recommended

Visit us at kalrez.com

dupont.com



The information set forth herein is furnished free of charge, is based on technical data that DuPont believes to be reliable, and represents typical values that fall within the normal range of properties. This information relates only to the specific material designated and may not be valid for such material used in combination with other materials or in other processes. It is intended for use by persons having technical skill, at their own discretion and risk. This information should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards and comply with applicable law. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

CAUTION: Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with the DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative.

DuPont's sole warranty is that our products will meet our standard sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DUPONT SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, MERCHANTABILITY, OR NON-INFRINGEMENT. DUPONT DISCLAIMS LIABILITY FOR ANY SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES.

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, ® or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.

© 2019 DuPont. All rights reserved.

(06/05) Reference KZE-H90161-00-H0719